

QUALPOL

HDPE FUSIBLE PRESURE



Raw Material

Manufactured using only virgin 4710 resin and NSF approved colorant.

Supply Options

Available in coils, straight lengths, or on reels.

JOINTLESS CONSTRUCTION

4710 HDPE



**HEAT
FUSION
READY**

SPECIFICATIONS



Produced to ASTM
D3035 and NSF14
standards

SDR			3/4"	1"	1 1/4"	1 1/2"	2"	3"	4"
333 PSI SDR7	OD		1.050	1.315	1.660	1.900	2.375	3.500	4.500
	ID		0.730	0.920	1.160	1.325	1.656	2.440	3.137
	WALL		0.150	0.188	0.237	0.271	0.339	0.500	0.643
	WT/FT		0.190	0.290	0.460	0.610	0.950	2.060	3.400
250 PSI SDR9	OD		1.050	1.315	1.660	1.900	2.375	3.500	4.500
	ID		0.818	1.023	1.292	1.478	1.847	2.722	3.500
	WALL		0.117	0.146	0.184	0.211	0.264	0.389	0.500
	WT/FT		0.150	0.230	0.370	0.490	0.760	1.650	2.720
200 PSI SDR11	OD		1.050	1.315	1.660	1.900	2.375	3.500	4.500
	ID		0.860	1.075	1.358	1.554	1.943	2.864	3.682
	WALL		0.095	0.120	0.151	0.173	0.216	0.318	0.409
	WT/FT		0.120	0.190	0.310	0.410	0.640	1.400	2.250
160 PSI SDR 13.5	OD		0.000	1.315	1.660	1.900	2.375	3.500	4.500
	ID		0.000	1.121	1.414	1.618	2.023	2.982	3.834
	WALL		0.000	0.097	0.123	0.141	0.176	0.259	0.330
	WT/FT		0.110	0.160	0.260	0.340	0.530	1.160	1.910
125 PSI SDR 17	OD		-	-	-	-	2.375	3.500	4.500
	ID		-	-	-	-	2.080	3.088	3.970
	WALL		-	-	-	-	0.140	0.206	0.265
	WT/FT		-	-	-	-	0.420	0.910	1.510